Recal POTAPTO 2 1 DEC 2004

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization

International Bureau



10/518829 /

(43) International Publication Date 8 January 2004 (08.01.2004)

PCT

(10) International Publication Number WO 2004/003960 A1

(51) International Patent Classification⁷: 29/87

H01J 29/86,

(21) International Application Number:

PCT/IB2003/002323

(22) International Filing Date: 27 M

27 May 2003 (27.05.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data: 02077563.1

28 June 2002 (28.06.2002) E

- (71) Applicant (for all designated States except US): KONIN-KLIJKE PHILIPS ELECTRONICS N.V. [NL/NL]; Groenewoudseweg 1, NL-5621 BA Eindhoven (NL).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): KHALIL, Mohammed [FR/NL]; c/o Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL). KUIN, Georgius, P., J. [NL/NL]; c/o Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).


- (74) Agent: VAN WERMESKERKEN, Stephanie, C.; Philips Intellectual Property & Standards, Prof. Holstlaan 6, NL-5656 AA Eindhoven (NL).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

with international search report

[Continued on next page]

(54) Title GLASS PANEL FOR A CATHODE RAY TUBE



(57) Abstract: The invention relates to a glass panel (2) for a cathode ray tube, in particular a real flat panel, comprising a substantially rectangular display window (5) having an upright edge (6) along its periphery. The glass panel (2) meets the following stress distribution criterion: $S_{\text{icor}} > S_{\text{icf}}$ where Sicor is a compressive inside surface stress at a corner (19, 20, 21, 22) of the display window (5) and Sicf is a compressive inside surface stress at a center face (25) of the display window (5). Preferably, the ratio of $S_{\text{icor}} / S_{\text{icf}}$ is higher than or equal to 1.05 and lower than or equal to 2.0. As a result of this particular stress distribution, the strength and the mechanical safety of the panel (2) are increased, so that the glass thickness of the panel (2) and/or thermal processing speeds may be reduced.